

IN THE SPECIFICATION:

Please amend the Specification by amending the paragraph bridging pages 7 to 8 to read as follows:

The reactive filter material is activated carbon, which is in the form of granules 6. Wax in the form of tiny sheathed beads combined to form larger pellets is added as a phase change material 7', 7" to the granules 6 of the activated carbons. These pellets may contain in particular additional filler material having a good conductivity with a volume amount of approximately 5% to 15% based upon the total volume. For the cohesion of the individual components within the pellets, a binder may be provided in an amount of approximately 5% to 10%, for example.